

# Electric activity of different magnetic textures

**D. I. Khomskii**

**Koeln University, Germany**

- **Polarization in frustrated Mott insulators**
- **Monopoles and dipoles in spin ice**
- **Dipoles at spin fragmentation**
- **Dipoles on spin spirals (both ways)**
- **Dipoles on spin waves**
- **Magnetic monopoles in magnetoelectrics**
- **Electric activity of skyrmions**

# ● Electronic Orbital Currents and Polarization in Mott Insulators

L.N. Bulaevskii, C.D. Batista, M. Mostovoy and D. Khomskii

PRB **78**, 024402 (2008)

D. Khomskii

J.Phys.-Cond. Mat. **22**, 164209 (2010)

## Mott insulators

$$H = - \sum_{ij\sigma} t_{ij} (c_{i\sigma}^+ c_{j\sigma} + c_{j\sigma}^+ c_{i\sigma}) + \frac{U}{2} \sum_i (n_i - 1)^2,$$

Standard paradigm: for  $U \gg t$  and one electron per site electrons are localized on sites. All charge degrees of freedom are **frozen out**; only spin degrees of freedom remain in the ground and lowest excited states

$$H_S = \frac{4t^2}{U} (S_1 \cdot S_2 - 1/4).$$

## Not the full truth!

For certain spin configurations there exist in the ground state of strong Mott insulators **spontaneous electric currents** (and corresponding orbital moments)!

For some other spin textures there may exist a **spontaneous charge redistribution**, so that  $\langle n_i \rangle$  is not 1! This, in particular, can lead to the appearance of a spontaneous **electric polarization** (a purely *electronic mechanism of multiferroic behaviour*)


These phenomena, in particular, appear in **frustrated systems**, with **scalar chirality** playing important role

Often complicated ground states; sometimes  $\langle \mathbf{S}_i \rangle = 0$  

 spin liquids

Some structures, besides  $\langle \mathbf{S}_i \rangle$ , are characterized by:

Vector chirality




$$[\mathbf{S}_i \times \mathbf{S}_j]$$

Scalar chirality

$$\chi_{123} = \mathbf{S}_1 [\mathbf{S}_2 \times \mathbf{S}_3]$$

- solid angle

$\chi$  may be + or - :



But what is the scalar chirality physically?



What does it couple to?

How to measure it?

Breaks time-reversal-invariance **T** and inversion **P** - like currents!

→  $\chi_{123} \neq 0$  means spontaneous circular electric current  
 $j_{123} \neq 0$  and orbital moment  $L_{123} \neq 0$

$$L_{123} \propto j_{123} \propto \chi_{123}$$



Couples to magnetic field:

$$-LH \sim -\chi H$$


# Spin current operator and scalar spin chirality

- Current operator for Hubbard Hamiltonian on bond  $ij$ :

$$I_{ij} = \frac{iet_{ij}r_{ij}}{\hbar r_{ij}} \sum_{\sigma} (c_{i\sigma}^+ c_{j\sigma} - c_{j\sigma}^+ c_{i\sigma}).$$

- Projected current operator: odd # of spin operators, scalar in spin space. For smallest loop, triangle,


$$I_{S,12}(3) = \frac{r_{ij}}{r_{ij}} \frac{24et_{12}t_{23}t_{31}}{\hbar U^2} [S_1 \times S_2]_g S_3.$$



- Current via bond 23

$$I_{S,23} = I_{S,23}(1) + I_{S,23}(4).$$

- On bipartite  $nn$  lattice  $I_S$  is absent.




# Orbital currents in the spin ordered ground state $\langle \mathbf{S}_i \rangle \neq 0$

- Necessary condition for orbital currents is nonzero average chirality

$$\chi_{12,3} = [\mathbf{S}_1 \times \mathbf{S}_2] \cdot \mathbf{g}\mathbf{S}_3, \quad \langle \chi_{ij,k} \rangle \neq 0.$$


- It may be inherent to spin ordering or induced by magnetic field



Triangles with  $\pm$  chirality

Tetrahedra with [111] anisotropy

# Boundary and persistent current




Boundary current in  
gaped 2d insulator

## ● Spin-dependent electronic polarization

Charge operator on site  $i$ :  $Q_i = e \sum_{\sigma} c_{i\sigma}^+ c_{i\sigma}$ .

Projected charge operator  $n_{S,i} = P e^S n_i e^{-S} P$ ,

$$\langle n_1 \rangle = 1 + \delta n_1 = 1 - 8 \left( \frac{t}{U} \right)^3 [\mathbf{S}_1 (\mathbf{S}_2 + \mathbf{S}_3) - 2\mathbf{S}_2 \mathbf{S}_3]$$




Polarization on triangle  $\mathbf{P}_{123} = e \sum_{i=1,2,3} n_{S,i} \mathbf{r}_i$ ,  $\sum_i n_{S,i} = 3$ .

Charge on site  $i$  is sum over triangles at site  $i$ .

# Electronic polarization on triangle

---


$$\langle n_1 \rangle = 1 + \delta n_1 = 1 - 8 \left( \frac{t}{U} \right)^3 [\mathbf{S}_1 (\mathbf{S}_2 + \mathbf{S}_3) - 2\mathbf{S}_2 \mathbf{S}_3]$$



**Purely electronic mechanism of multiferroic behavior!**

# Charges on kagome lattice

---



1/3 magnetization  
plateau:


Charge ordering for spins  
1/3 in magnetic field:  
spin-driven CDW

- Typical situation at the magnetization plateaux!

● Diamond chain (azurite  $\text{Cu}_3(\text{CO}_3)_2(\text{OH})_2$ )




spin singlet





-will develop S-CDW

● Saw-tooth (or delta-) chain



Net polarization



Net polarization









Figure 1. (a) Structure of euchroite, (b) schematic view of the delta chain.



# ● Monopoles and dipoles in spin ice

Pyrochlore: Two interpenetrating metal sublattices

● Ho (R)  
● Ti (M)



nature  
COMMUNICATIONS

ARTICLE


Received 23 Feb 2012 | Accepted 14 May 2012 | Published 19 Jun 2012

DOI: 10.1038/ncomms1904


Electric dipoles on magnetic monopoles in spin ice

D.I. Khomskii


# Excitations creating magnetic monopole (Castelnovo, Moessner and Sondhi)



M J P Gingras Science 2009;326:375-376




2-in/2-out: net magnetic charge inside tetrahedron zero




3-in/1-out: net magnetic charge inside tetrahedron  $\neq 0$   
 – **monopole** or **antimonopole**

# ★ Dipoles on tetrahedra:


D.I.Khomskii  
Nature Comm. 3, 904 (2012)




4-in or 4-out:  
 $\mathbf{d}=\mathbf{0}$



2-in/2-out (spin  
ice):  $\mathbf{d}=\mathbf{0}$




3-in/1-out or 1-in/3-out  
(monopoles/antimonopoles):  $\mathbf{d} \neq \mathbf{0}$





$$\langle n_1 \rangle = 1 + \delta n_1 = 1 - 8 \left( \frac{t}{U} \right)^3 [\mathbf{S}_1 (\mathbf{S}_2 + \mathbf{S}_3) - 2\mathbf{S}_2 \mathbf{S}_3]$$

For 4-in state: from the condition  $\mathbf{S}_1 + \mathbf{S}_2 + \mathbf{S}_3 + \mathbf{S}_4 = 0$   $\delta n_1 = 0$ . Change of  $\mathbf{S}_1 \rightarrow -\mathbf{S}_1$  (3-in/1-out, *monopole*) gives nonzero charge redistribution and  $\mathbf{d} \neq 0$ .

Charge redistribution and dipoles are *even* functions of  $\mathbf{S}$ ; inversion of all spins does not change direction of a dipole:  Direction of dipoles on monopoles and antimonopoles is *the same*: e.g. from the center of tetrahedron to a "special" spin

$H \parallel [111], >H_c$

**Monopoles/antimonopoles at every tetraheder, staggered**



$H \parallel [111]$




Fig. 1. Phase diagram of  $\text{Dy}_2\text{Ti}_2\text{O}_7$  in a  $[111]$  magnetic field, determined by magnetization and specific heat measurements. The dashed line

# Electric dipoles on magnetic monopoles

$H \parallel [111]$


Experimental evidence:

D.I. Khomskii, *Nature Comm.*, **3**, 1 (2012)



PHYSICAL REVIEW B 72, 144422 (2005)

Magnetodielectric response of the spin-ice  $Dy_2Ti_2O_7$

Masafumi Saito,<sup>1</sup> Ryuji Higashinaka,<sup>1</sup> and Yoshiteru Maeno<sup>1,2,\*</sup>



[Aoki et al., JPSJ (2004)]





-> Anomalies at and above transition  
into monopole order  
But: frequency dependent !

-> dynamics ...

(large offset in  $\epsilon'$  due to titanium sublattice)

# Monopole dynamics in $\text{Dy}_2\text{Ti}_2\text{O}_7$



->  $v_p = 1/2\pi\tau$   
 recaptures features of  
 "monopole condensation"  
 -> slowing down outside  
 crossover lines

-> Critical **speeding up** above critical end-point !!!

# ● Spin fragmentation

PHYSICAL REVIEW X 4, 011007 (2014)

---


## Magnetic-Moment Fragmentation and Monopole Crystallization

M. E. Brooks-Bartlett,<sup>1</sup> S. T. Banks,<sup>1</sup> L. D. C. Jaubert,<sup>2</sup> A. Harman-Clarke,<sup>1,3</sup> and P. C. W. Holdsworth<sup>3,\*</sup>

not, however, define the entire moment density, which can have two contributions through a Helmholtz decomposition. The first  $\vec{M}_m$  is the gradient of a scalar potential and provides the magnetic charge; the second  $\vec{M}_d$  is a dipolar field, can be represented as the curl of a vector potential, and is divergence free [21,22]:

$$\vec{M} = \vec{M}_m + \vec{M}_d = \vec{\nabla} \psi(r) + \vec{\nabla} \wedge \vec{Q}. \quad (1)$$

**The main point: one can have monopole crystal, with LRO, but simultaneously spins themselves disordered**



Manifestation in neutron scattering: coexistence of diffuse background (due to disordered spins) and LRO signal of monopole crystal (pinch points)




FIG. 4. Simulated unpolarized neutron-scattering structure factors  $S(Q)$  for the pyrochlore monopole crystal (left) and for in-plane scattering from kagome ice (right). The pyrochlore  $S(Q)$  has been calculated by averaging over 2000 distinct monopole-crystal ground

# Fragmentation of magnetism in artificial kagome dipolar spin ice

Benjamin Canals<sup>1,2</sup>, Ioan-Augustin Chioar<sup>1,2</sup>, Van-Dai Nguyen<sup>1,2</sup>, Michel Hehn<sup>3</sup>, Daniel Lacour<sup>3</sup>, François Montaigne<sup>3</sup>, Andrea Locatelli<sup>4</sup>, Tevfik Onur Menteş<sup>4</sup>, Benito Santos Burgos<sup>4</sup> & Nicolas Rougemaille<sup>1,2</sup>

## LETTERS

PUBLISHED ONLINE: 4 APRIL 2016 | DOI: 10.1038/NPHYS3710

nature  
physics



## Observation of magnetic fragmentation in spin ice

S. Petit<sup>1\*</sup>, E. Lhotel<sup>2\*</sup>, B. Canals<sup>2</sup>, M. Ciomaga Hatnean<sup>3</sup>, J. Ollivier<sup>4</sup>, H. Mutka<sup>4</sup>, E. Ressouche<sup>5</sup>, A. R. Wildes<sup>4</sup>, M. R. Lees<sup>3</sup> and G. Balakrishnan<sup>3</sup>

### Magnetic charge injection in spin ice: a new way to fragmentation


E. Lefrançois,<sup>1,2,\*</sup> V. Cathelin,<sup>2</sup> E. Lhotel,<sup>2</sup> J. Robert,<sup>2</sup> P. Lejay,<sup>2</sup> C. V. Colin,<sup>2</sup> B. Canals,<sup>2</sup> F. Damay,<sup>3</sup> J. Ollivier,<sup>1</sup> B. Fåk,<sup>1</sup> L. C. Chapon,<sup>1</sup> R. Ballou,<sup>2</sup> and V. Simonet<sup>2</sup>

# Dipole activity of spin fragmentation materials?




→ - dipole moments.

(a)




(b)



# ● Dipoles on spirals

Cycloidal SDW

$$\bar{\mathbf{P}} \propto [\mathbf{e}_3 \times \mathbf{Q}]$$





Katsura, Nagaosa and Balatsky, 2005  
Mostovoy 2006

-- gives dipoles/polarization on the Neel domain walls

# ● Electric dipoles at domain walls


Was already observed for Neel domain walls in ferromagnets (cf. spiral multiferroics):






**Fig. 2** The effect of electric field in the vicinity of electrode (1) on magnetic domain wall (2) in the films of ferrite garnets: a) initial state b) at the voltage of +1500 V applied


# ● Inhomogeneous electric field in spin ice





In  $\mathbf{H} // [001]$ :

Monopoles:  $d^z > 0$   
Antimonopoles:  $d^z < 0$



# Chiral magnetic order at surfaces driven by inversion asymmetry

M. Bode<sup>1,†</sup>, M. Heide<sup>2</sup>, K. von Bergmann<sup>1</sup>, P. Ferriani<sup>1</sup>, S. Heinze<sup>1</sup>, G. Bihlmayer<sup>2</sup>, A. Kubetzka<sup>1</sup>, O. Pietzsch<sup>1</sup>, S. Blügel<sup>2</sup> & R. Wiesendanger<sup>1</sup>

PRL 101, 027201 (2008)

PHYSICAL REVIEW LETTERS

week ending  
11 JULY 2008



## Atomic-Scale Spin Spiral with a Unique Rotational Sense: Mn Monolayer on W(001)

P. Ferriani,<sup>1,\*</sup> K. von Bergmann,<sup>1</sup> E. Y. Vedmedenko,<sup>1</sup> S. Heinze,<sup>1</sup> M. Bode,<sup>1,†</sup> M. Heide,<sup>2</sup> G. Bihlmayer,<sup>2</sup> S. Blügel,<sup>2</sup> and R. Wiesendanger<sup>1</sup>



<sup>1</sup>*Institute of Applied Physics, University of Hamburg, Jungiusstrasse 11, 20355 Hamburg, Germany*

<sup>2</sup>*Institut für Festkörperforschung, Forschungszentrum Jülich, 52425 Jülich, Germany*

(Received 15 April 2008; published 7 July 2008)

Using spin-polarized scanning tunneling microscopy we show that the magnetic order of 1 monolayer Mn on W(001) is a spin spiral propagating along  $\langle 110 \rangle$  crystallographic directions. The spiral arises on the atomic scale with a period of about 2.2 nm, equivalent to only 10 atomic rows. *Ab initio* calculations identify the spin spiral as a left-handed cycloid stabilized by the Dzyaloshinskii-Moriya interaction, imposed by spin-orbit coupling, in the presence of softened ferromagnetic exchange coupling. Monte Carlo simulations explain the formation of a nanoscale labyrinth pattern, originating from the coexistence of the two possible rotational domains, that is intrinsic to the system.

# rotation direction of spin spiral



6 out of 6 independent islands: same rotational sense  
→ DM-driven spin spiral


Simple explanation: at the surface there is a drop of a potential (work function, double layer)

I.e. there is an electric field  $\mathbf{E}$ , or polarization  $\mathbf{P}$  perpendicular to the surface

By the relation


$$\bar{\mathbf{P}} \propto [\mathbf{e}_3 \times \mathbf{Q}]$$

there will appear magnetic spiral with certain sense of rotation, determined by  $\mathbf{P}$



# ● Electric dipole carried by the usual spin wave

D.Khomskii, *Physics (Trends)* **2**, 20 (2009)





*Physics (Trends)* **2**, 20 (2009)

FIG. 5: How polarization emerges in a spin wave (magnon). (a) The classical picture of a spin wave in a ferromagnet: the spin (red arrow) precesses about a fixed axis (blue). The deviation is measured by the black arrows. (b) According to Eq. (1), as a spin-wave packet propagates along  $Q$ , it will also carry an electric dipole moment. (Illustration: Alan Stonebraker)

# ● Magnetic monopoles in magnetoelectrics ?

Charge inside of of ME material:  $\mathbf{M}_i = \alpha_{ij} \mathbf{E}_j$ ,  $\mathbf{H} = 4\pi\mathbf{M}$

Let  $\alpha_{ij} = \alpha\delta_{ij}$ , diagonal: magnetic field outside of the charge looks like a field of a magnetic monopole  $\mu = 4\pi\alpha e$



Moving electron  $\longrightarrow$  moving monopole.

Electron in a magnetic field: force  $\mathbf{F} = \mu\mathbf{H} = 4\pi\alpha e\mathbf{H}$

(But one can also consider it as an action of the electric field created in magnetoelectric material on the electric charge:  $\mathbf{E} = 4\pi\alpha\mathbf{H}$ ,  $\mathbf{F} = \mathbf{E}e = 4\pi\alpha e\mathbf{H}$  )

**Other possible effects ?** (how to find, to measure such monopoles)

"**Electric Hall effect**": if electric charge  $e$  moving in  $\mathbf{H}$  gives a Hall effect, a monopole moving in electric field will do the same





Figure 2: Motion of a magnetic monopole  $b$ , accompanying electric charge  $e$ , in a perpendicular electric field. The force  $b[\mathbf{v} \times \mathbf{E}]$  will bend the trajectory of this object, leading to an “electric Hall effect”.

But one can also explain this effect as the usual Hall effect in an effective magnetic field  $\mathbf{B} \sim \alpha \mathbf{E}$

Search for the magnetic monopole at a magnetoelectric surface

[Q. N. Meier](#), [M. Fechner](#), [T. Nozaki](#), [M. Sahashi](#), [Z. Salman](#), [T. Proschka](#), [A. Suter](#), [P. Schoenherr](#), [M. Lilienblum](#), [P. Borisov](#), [I. E. Dzyaloshinskii](#), [M. Fiebig](#), [H. Luetkens](#), [N. A. Spaldin](#) Phys. Rev. X 9, 011011 (2019)



Qi, X. L., Li, R., Zang, J. & Zhang, S. C. Inducing a magnetic monopole with topological surface states. Science 323, 1184–1187 (2009).

Zang, J. & Nagaosa, N. Monopole current and unconventional Hall response on topological insulators. Phys. Rev. B81, 245125

# ● Magnetic vortices as magnetoelectrics

PRL 102, 157203 (2009)

PHYSICAL REVIEW LETTERS

week ending  
17 APRIL 2009

## Superexchange-Driven Magnetoelectricity in Magnetic Vortices

Kris T. Delaney,<sup>1</sup> Maxim Mostovoy,<sup>2</sup> and Nicola A. Spaldin<sup>1</sup>





FIG. 1 (color online). (a) A magnetic vortex carrying a monopole moment. The thin solid arrows indicate the spin orientation, while the thick open arrows show the local polarization vector. (b) A magnetic field applied to the vortex shown in (a) induces a net polarization along the field direction. (c) A magnetic vortex with a toroidal moment. (d) A magnetic field applied to (c) induces an electric polarization perpendicular to the field.

# ● Skyrmions in magnetic crystals


“Toroidal” (Bloch) skyrmion

Should give magnetoelectric effect with  $\mathbf{P} \perp \mathbf{H}$




$$\mathbf{P} \sim \mathbf{r}_{ij} \times [\mathbf{S}_i \times \mathbf{S}_j]$$

## “Radial” (Neel) skyrmion




Should give magnetoelectric effect with  $P \parallel H$


# Skyrmions in inhomogeneous electric field?



# Skyrmions in inhomogeneous electric field?



# Skyrmions in inhomogeneous electric field?



# Electric-field-driven switching of individual magnetic skyrmions

Pin-Jui Hsu, André Kubetzka, Aurore Finco, Niklas Romming, Kirsten von Bergmann\*  
and Roland Wiesendanger


- generation of skyrmions on a surface by the STM tip with the electric voltage. Only for one polarity.

SPINTRONICS

## Electric control of skyrmions

The creation and destruction of magnetic whirls by the application of an electric field may be the basis for novel memory technologies.

Achim Rosch



# CONCLUSIONS

**Electric activity of many different magnetic textures, and even of spin waves.**